

510

LIME CEMENT PRIMER

866

CEMENT LIME MORTAR
WITH PERLITE GRANULES**Description and field of use:**

Factory-prepared base mortar for walls and ceilings brick, concrete and light concrete blocks.

Composition:

- Cement
- Lime
- Fine lime sand
- filler
- Additives
- Slight addition of organic (Milfas 866)

Properties:

- Abundance
- Workability
- Good adhesion

Surface preparation:

The surface has to be dry, without dust or dirt. It is necessary to waterproof all highly absorbent, light concrete and other outer surfaces with MILFAS ACRYLIC PRIMER (grund).

Material preparation and processing:

Mix bag content with water until it becomes homogeneous. Prepared mass is applied manually or mechanically in the required thickness. Finishing is possible in 3-4 hours.

Processing conditions:

Temperature of surface and air should be from 5 to 30 C. Surfaces directly exposed to sunlight or strong wind should be leached with water and protected with protective curtains.

Consumption:

Milfas 510
cca 12 kg/m² for layer thk=10 mm

Milfas 866
cca 11 kg/m² for layer thk=10 mm

Packaging:

35 kg bag

Storage:

Storable for 6 months in original packaging on wooden grate in dry place.

Safety warning:

Irritant. Protect skin, mucous membrane and eyes.

**mili evi** d.o.o. Kreševo, BiH

Technical instructions provided in this publication are based on our experience and are provided in order to achieve the optimal results in using this product. For damages caused by wrong choice of product, its irregular application or low quality work we do not accept responsibility. This data sheet complements and replaces all previous editions. Milicevic Ltd. Kresevo reserves the right to all subsequent changes and additions.