

Description and field of use:

Factory prepared mass for leveling interior walls and ceilings of all kinds of fine materials, concrete without stucco, plaster and fiber-cement panels, correction errors, filling holes, cracks and scratches. Milfas 351 is designed for interior use only.

Composition:

- Cement (Milfas 441 grey)
- White cement (Milfas 441 white)
- Plaster (Milfas 351)
- Fine calcareous sand
- Filler
- Additives

Properties:

- Abundance
- Good adhesion
- Hydrophobicity
- Constancy
- Firmness

Surface preparation:

The surface has to be clean, without frost, loose parts, coarse enough.

Material preparation and processing:

Mix content of the bag in clean container in approximate proportion 1:3.Mix until it becomes completely homogenous without lumps. Leave it for 5-10 minutes, mix again and it is ready for use. Mass is applied with steel trowel in 2-3 mm layers and finely smoothens. To level bigger bumps apply leveling in multiple layers applying new layer on the dried one. When the mass is completely dry hone smaller irregularities. Dry for 12 hours (T= 20 C, humidity = 65%, it has to be dry on touch).

Processing conditions:

Temperature of the surface and air should not be lower than 5 C. During drying process protect form frost for at least 3 days.

Consumption:

Milfas 441 :
Cca 1 kg/m² for layer thk=1 mm
Milfas351:
Cca 1,2 kg/m² for layer thk=1mm

Packaging:

25 kg bag

Storage:

Storable for 12 months in original packaging on wooden grate in dry place.

Safety warning:

Irritant. Protect skin, mucous membrane and eyes.



mili evi d.o.o. Kreševo, BiH

Technical instructions provided in this publication are based on our experience and are provided in order to achieve the optimal results in using this product. For damages caused by wrong choice of product, its irregular application or low quality work we do not accept responsibility. This data sheet complements and replaces all previous editions. Milicevic Ltd. Kresevo reserves the right to all subsequent changes and additions.